

		EN16523-1:2015+A1 :2018 1 ▶ 6 10 mn ▶ 480 mn	EN ISO 374-4:2019
D03	(K) - CAS 1310-73-2	6 > 480 min	-4.7 %
D04	(L) - CAS 7664-93-9	4 > 120 min	-10.1 %
D13	(M)- CAS 7697-37-2	3 > 60 min	-9.7 %
D14	(N) – CAS 64-19-7	3 > 60 min	1.2 %
D16	(P) - CAS 7722-84-1	5 > 240 min	-5.8 %
D18	(T) – CAS 50-00-0	5 > 240 min	-12.2 %